

OFFICE OF NAVAL RESEARCH

Contract NOO014-75-C-0883

Task No. NR 051-539

TECHNICAL REPORT NO. 77-03

Far Infrared Studies of Ion Clustering in Ionomers

by

George B. Rouse, Andreas T. Tsatsas, Adi Eisenberg and William M. Risen, Jr.

Prepared for Publication

in


Journal of Polymer Science (Polymer Physics Section)

Department of Chemistry Brown University Providence, Rhode Island 02912

26 December 1977

Reproduction in whole or in part is permitted for any purpose of the United States Government

Approved for Public Release: Distribution Unlimited



SECURITY CLASSIFICATION OF THIS PAGE (HEAD Date Entered) READ INSTRUCTIONS BEFORE COMPLETING FORM REPORT DOCUMENTATION PAGE 2. GOVT ACCESSION NO. 3. RECIPIENT'S CATALOG NUMBER 1. REPORT NUMBER 4. TITLE (and Subtitle) TYPE OF REPORT & PERIOD COVERED Trechnical Report 277 Far Infrared Studies of Ion Clustering in Ionomers. 4 TR-77-03 CONTRACT OR GRAN NUMBER(1) . AUTHOR(s) 000 14-75-C-0883 George B./Rouse, Andreas T./Tsatsas, Adi /Eisenberg William M. Risen, Jr. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry Brown University, Providence, R. I. 02912 11. CONTROLLING OFFICE NAME AND ADDRESS REPORT DATE 26 Dec 77 Office of Naval Research Department of the Navy 14. MONITORING AGENCY NAME & ADDRESS(If different from Controlling Office) IE. SECURITY CLASS 154. DECLASSIFICATION DOMNURADING 16. DISTRIBUTION STATEMENT for this Repart Approved for Public Release: Distribution Unlimited 17. DISTRIBUTION STATEMENT (of the eboract entered in Block 20, if different from Report) 18. SUPPLEMENTARY NOTES 13. KEY WORDS (Continue on reverse side if necessary and identity by block number) ionic clusters, ionomers, infrared spectra, Raman spectra, ion motion STRACT (Continue or reverse aide if pecasery and identity by block number) Direct evidence for the existence of ion clusters in ionomers has been found through the investigation of the far infrared spectra of (PSMA) alkali metal ionomers of polystyrene methacrylic acid measured as a function of ionic content. The Co existence of two kinds of cationcontaining environments, multiplets and clusters, has been shown for sodium PSMA ionomers, in which the two must be present simultaneously above 3.9 mole % of ionic groups. The study includes H^+ , Na^+ , Cs^+ , and Ba PSMA ionomers in the 50-500 cm⁻¹ region. DD 1 JAN 73 1473 EDITION OF I NOV 65 IS OBSOLETE S/N 0102-014-6601 SECURITY CLASSIFICATION OF THIS PAGE (When Date Enteres Contribution from the Metcalf Research Laboratory, Department of Chemistry, Brown University, the Inorganic Chemistry Laboratory, University of Athens and the Department of Chemistry, McGill University

the way of the second s

Far Infrared Studies of Ion Clustering in Ionomers

by

George B. Rouse¹, Andreas T. Tsatsas², Adi Eisenberg³ and William M. Risen, Jr.^{1,4}

UNANNOUTICED JUSTI ICATION BY DISTRIBUTION/AYAIT ADITITY COTES	UNANNOUTICED JUSTI TOATION BY DISTRIBUTION/AVAITABLETTY COTES	UNANNOUTICED JUSTI ICATION BY DISTRIBUTION/AYAI ADUITY COTES	NTIS	Wile Saction
BY DISTRIBUTION/AYAN ADD ITY COLES	BY DISTRIBUTION/AVAILADILITY COTES	BY DISTRIBUTION/AVAILADILITY COTES		Buff Section [
BY DISTRIBUTION/AYAN ABOUTY COTES	BY Distribution/ayan add ity codes	BY Distribution/ayah adi ity codes		
DISTRIBUTION/AVAI ABI ITY CCTES	DISTRIBUTION/AVAILABLE ITY COSES	DISTRIBUTION/AVAILABILITY CCCES	JUSTI ICA TO	V
	Dist.	Dist	BY DISTRIBUTION	WAYAWAR ARE ITY COLES
A	(A)		DISTRIBUTION	N/AYAN ABI' ITY COZES 22- Gla

Introduction

The state of aggregation of ionic groups in solid state ionomers, ion-containing polymers, is known to be important in determining the mechanical and rheological properties of the materials. These materials usually are formed by replacing the H⁺ ions in acidic copolymers, such as polyethylene methacrylic acid copolymers, by metal ions. In materials of low dielectric constant and at low ionic concentration, the ions (metal ions and ionic sites on the polymer) aggregate to some degree to form ion-pairs and multiplets (several ion pairs) which act as transient crosslinks. As the concentration of ionic groups increases many of the ions, along with some non-ionic material, come together to form larger clusters. These clusters act not only as crosslinks but also as re-enforcing fillers of microcrystallites. Clearly, then, the physical properties of such ionomers not only are very different from those of the related non-ionic polymers but are dependent on the ionic concentration.

Eisenberg 5-7 and others 8-10 have reviewed the physical properties of ionomers and the extensive studies concerning ionomers and their formation of multiplets and clusters. No vibrational spectroscopic evidence for the existence of the clusters has been reported.

Based on our previous experience with non-aqueous electrolyte solutions 11, polyethylene methacrylic acid ionomers 2 and ionic glasses 13, we have used far infrared spectroscopy to probe cation-cation and cation-site interactions in polystyrene methacrylic acid ionomers as a function of cation and ion-site concentration in an attempt to identify spectroscopic evidence of domain formation. More specifically the attempt is to identify a far infrared band due to the vibration of a higher order cluster.

Experimental

Polystyrene methacrylic acid (PSMA) ionomers, of the form

$$(CH_2-CH)_n \cdot (CH_2-C)_m - (\frac{m}{k})M^{+k}$$

ことの はない これのはない

where M+k is Na+, Cs+ of Ba+2 were prepared by the methods of Eisenberg and Navratil. Labelling of materials is by a number giving the mole % of methacrylic acid comonomer followed by letters (H, Na, Cs, Ba) in parentheses indicating the acidic or metalated copolymer and with the letter & or h to indicate low (50,000-70,000) of high (ca 400,000) molecular weight respectively. For example, 4.6 (Na)h is the sodium-form ionomer of the PSMA copolymer with 4.6 mole % acid groups and a molecular weight of about 400,000. Table I gives the acid concentrations of the samples studied in mole %, n/m ratio and in terms of carbon atoms between acid groups for the PSMA ionomers. The degree of replacement of carboxylic hydrogens by M+k was 99-100% in the samples studied. This can be ascertained from the mid-infrared spectra of the ionomers.

The far infrared spectra in the region 50-450 cm⁻¹ of 0.05-0.20 mm thick films of PSMA ionomers were recorded with a Digilab FTS-14 Fourier transform far infrared spectrometer at ambient temperature. Each spectrum was recorded several times with a reproducibility of 1% in absorbance and with ca. 2 cm⁻¹ resolution.

Spectral Results

The far infrared spectra (50-450 cm⁻¹) of the low molecular weight PSMA ionomers containing Cs⁺, Ba⁺² and Na⁺ and the un-ionized form of the low molecular weight copolymer are shown in Figure 1. A dominant feature appears in

the Cs⁺, Ba⁺², and Na⁺ ionomer spectra which is not present in the spectra of the un-ionized form in the region below 300 cm⁻¹. This feature is a broad, well defined band which shifts from 250±5 cm⁻¹ for the Na⁺ ionomer to 185±5 cm⁻¹ for Ba⁺², to 115±5 cm⁻¹ for Cs⁺. Since these bands shift strongly with cation mass and charge, they must be due to cation-site vibrations and are assigned to cation motion in the anionic field of the copolymer¹².

はいいとあるというないと

In Figure 2 are shown the spectra of a series of Na⁺-form PSMA ionomers in which the anionic-group (acid) concentration is varied. As this concentration increases a band appears at <u>ca.</u> 170 cm⁻¹ on the low frequency side of the main Na⁺-motion band. In the band structure observed between 150 and 300 cm⁻¹ there are three bands. The one at about 250 cm⁻¹ is the primary cation motion band and, since it is present and dominant at low ionic concentration, it is assigned to the vibration of an aggregate involving few ions (low order multiplet). The middle of the three bands at ca 220 cm⁻¹, is a weak internal mode of the polymer. The 170 cm⁻¹ band is assigned to the vibrations of aggregates involving many cations and anionic sites close together.

This is entirely consistent with the formation of higher aggregates or clusters, because the oscillations of cations in such ion domains should have both a larger effective mass and lower effective force field (since the cationanion site attraction becomes increasingly screened). Thus, the vibrational frequency becomes lower than that of the simple cation-site or multiplet oscillators, which is consistent with a previous observation that in solution the ion motion frequencies for simple ion pairs is higher than that for higher aggregates.

All PSMA samples have a band at 405 cm⁻¹ which is of constant intensity after suitable corrections are made to account for varying sample thickness. This indicates that the band is due to a vibration along the polymer backbone since it is independent of ion content of the polymer. It might be assigned to either an out-of-plane bend of the benzene-type six-membered ring, as the one occurring at 405 cm⁻¹ in polystyrene, or to a C-C-C bend along the polymer chain. In straight chain alkanes the C-C-C bend is observed in the 350-450 cm⁻¹ frequency range¹⁵.

The same of the sa

The constancy of the 405 cm⁻¹ band is significant in light of the appearance of another band at 386 cm⁻¹ in the Na⁺ ionomer, 387 cm⁻¹ in the Ba⁺² and 381 cm⁻¹ in Cs⁺. This band is absent in the acid form, is not observed in the 0.6 (Na)& sample, but increases in intensity as the ion concentration increases (see Figure 2), which suggests that the vibration giving rise to this band is associated with the anion site. Two vibrational modes, clearly coupled, which meet this criterion, are C-C-O and the O-C-O bending motions, both modes of the carboxylate group.

Discussion

It is clear from the interpretation of the far infrared data that as the concentration of ionic sites increases the cation finds itself in more than one kind of environment. If at very low ionic site concentrations the sodium ion and the carboxylate ion from low order multiplets involving 1-4 cations plus anionic sites, the vibration of the cation in the force field of the anion and the hydrocarbon backbone give rise to the band at ca 250 cm⁻¹. With increasing ionic concentration, and much the same way as occurs in solution, higher aggregates are formed.

Whether the higher order aggregate band at 170 cm⁻¹ should be assigned to vibrating clusters, ¹⁶ or "ion drops", as defined by Holliday⁹, or other specific higher order aggregates cannot be asserted from our results. This is true dispite the fact that it might be attractive to assign the 170 cm⁻¹ band to vibrating ion drops because it is observed even for low (3.8 and 4.6 mole %) ion concentrations. Rheological, small angle X-ray scattering and time-temperature superposition evidence for clustering is apparent at ionic concentrations greater than 6 mole % for PSMA ionomers. However, our spectroscopic method may be more sensitive in detecting the existence of clusters than the above techniques and it detects them as they form and increase in concentration even before they become important rheologically.

The same of the sa

Within the vibrating higher order aggregate repulsions between mobile cations tend to alter the force field felt by the cation and cause low frequency ion motion vibrations. Interactions between cations adjacent to the carboxylate sites and these sites themselves are not greatly affected by this aggregation since the carboxylate band in the 400 cm⁻¹ region is not shifted.

The principal driving force for the formation of ion aggregates is the low dielectric constant of the backbone since the interionic attraction per cation changes little as aggregation proceeds. Whenever distances between ions are small enough, this driving force causes higher aggregates to be formed. The spectroscopic evidence, therefore, is consistent with the proposition that at low ionic concentrations small ion aggregates are formed, but at higher concentrations clustering of such aggregates to form ionic domains predominates.

Acknowledgements

This work was supported in part by the Office of Naval Research.

References

- 1. Department of Chemistry, Brown University, Providence, RI 02912 U.S.A.
- Inorganic Chemistry Laboratory, University of Athens, Navarinou 13A,
 Athens, Greece.
- 3. Department of Chemistry, McGill University, Montreal, Quebec, Canada
- 4. Author to whom correspondence should be addressed.
- 5. Eisenberg, A., Adv. Poly. Sci., 1967, 5, 59.

200

- 6. Eisenberg, A., Pure and Appl. Chem., 1976, 46, 171.
- Eisenberg, A. and King, M., "Ion-Containing Polymers" in "Polymer Physics",
 Vol. 2 Stein, R. S., ed., Academic Press, New York, 1977.
- 8. Otocka, E. P., J. Macromol. Sci.; Revs. Macromol. Chem., 1971, C5, 275.
- 9. Holiday, L., "Classification and General Properties of Ionic Polymers" in "Ionic Polymers" Holliday L., ed., Halsted Press, Barking, England, 1975.
- 10. Longworth, R. "Thermoplastic Ionic Polymers: Ionomers"in ibid.
- 11. Tsatsas, A. T., and Risen, W. M., Jr., J. Amer. Chem. Soc., 1970, 92, 1789.
- Tstasas, A. T., Reed, J. W. and Risen, W. M., Jr., J. Chem. Phys., 1971,
 3260.
- 13a. Exarhos, G. J. and Risen, W. M., Jr., Chem. Phys. Letters, 1971, 10, 484.
 - b. Exarhos, G. J., Miller, P. J. and Risen, W. M., Jr., J. Chem. Phys., 1974, 60, 4145.
- 14. Eisenberg, A. and Navratil, M., Macromolecules, 1973, 6, 604.
- 15. Snyder, R. G. and Schachtschneider, J. H., Spectrochim. Acta, 1962, 19, 85.
- 16. The term "cluster" implies ion-rich regions alternating with ion-poor regions. MacKnight 17 et al. has proposed a model consisting of a large central multiplet (ionic region) coated with a non ionic skin and surrounded by other multiplets or ion pairs. Eisenberg's model is that of a collection of interacting

multiplets separated by non-ionic material. (See references 7 [p. 31] and 9 [pp 30-36].)

 MacKnight, W. J., Taggart, W. P. and Stein R. S., J. Polym. Sci., Polym. Symp., 1974, 45, 113.

THE RESERVE OF THE PROPERTY OF THE PARTY OF

Table I. Acid Concentrations and Average Number of Carbon Atoms Between Acid Groups (a)

うまだ では、 というないというないはないにはなっている。

The Contract of the Contract o


mole %	n/m	ā
0.6	166	333
3.7	26	53
3.8	25	51
4.6	21	43
6.2	15	31
8.2	11	23


Figure Captions

The same of the sa

- Figure 1. Far infrared spectra of low molecular weight PSMA copolymer and ionomers.
- Figure 2. Far infrared spectra of a series of high molecular weight

 PSMA Na ionomers with varying mole % of carboxylic groups.





TECHNICAL REPORT DISTRIBUTION LIST

No. C	Copies	No. 1	Copie
Office of Naval Research Arlington, Virginia 22217 Attn: Code 472	2	Defense Documentation Center Building 5, Cameron Station Alexandria, Virginia 22314	12
Office of Naval Research Arlington, Virginia 22217 Attn: Code 1021P 1	6	U.S. Army Research Office P.O. Box 12211 Research Triangle Park, N.C. 27709 Attn: CRD-AA-IP	1
ONR Branch Office 536 S. Clark Street Chicago, Illinois 60605 Attn: Dr. Jerry Smith	1	Naval Ocean Systems Center San Diego, California 92152 Attn: Mr. Joe McCartney	1
ONR Branch Office 713 Broadway New York, New York 10003 Attn: Scientific Dept.	1	Naval Weapons Center China Lake, California 93555	
ONR Branch Office 1030 East Green Street Pasadena, California 91106 Attn: Dr. R. J. Marcus	1	Attn: Head, Chemistry Division Naval Civil Engineering Laboratory Port Hueneme, California 93041 Attn: Mr. W. S. Haynes	1
ONR Branch Office 760 Market Street, Rm. 447 San Francisco, California 94102 Attn: Dr. P. A. Miller	1	Professor O. Heinz Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
ONR Branch Office 495 Summer Street Boston, Massachusetts 02210 Attn: Dr. L. H. Peebles	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code Washington, D.C. 20380	RD-1)
Director, Naval Research Laborato Washington, D.C. 20390 Attn: Code 6100	ory 1	Office of Naval Research Arlington, Virginia 22217 Attn: Dr. Richard S. Miller	1
The Asst. Secretary of the Navy (Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	(R&D) 1		

Commander, Naval Air Systems Command Department of the Navy Washington, D.C. 20360 Attn: Code 310C (H. Rosenwasser) 1

THE REAL PROPERTY OF THE PROPERTY OF THE PARTY OF THE PAR

これが、 はないのと、 大きなないのではないのはないのである。 これないできないということ

TECHNICAL REPORT DISTRIBUTION LIST

No. Cop	pies	No. Cop	ies
Dr. D. A. Vroom IRT P.O. Box 80817 San Diego, California 92138	1	Dr. R. W. Vaughan California Institute of Technology Division of Chemistry & Chemical Engineering Pasadena, California 91125	1
Dr. G. A. Somorjai University of California Department of Chemistry Berkeley, California 94720	1	Dr. Keith H. Johnson Massachusetts Institute of Technology Department of Metallurgy and Materials Science	•
Dr. L. N. Jarvis		Cambridge, Massachusetts 02139	1
Surface Chemistry Division 4555 Overlook Avenue, S.W. Washington, D.C. 20375	1	Dr. M. S. Wrighton Massachusetts Institute of Technology Department of Chemistry Cambridge, Massachusetts 02139	1
Brown University			'
Department of Chemistry Providence, Rhode Island 02912	- 1	Dr. J. E. Demuth IBM Corp. Thomas J. Watson Research Center	
Dr. M. H. Chisholm Princeton University Chemistry Department		P.O. Box 218 Yorktown Heights, New York 10598	1
Princeton, New Jersey 08540	1	Dr. C. P. Flynn University of Illinois	
Dr. J. B. Hudson Rensselaer Polytechnic Institute Materials Division		Department of Physics Urbana, Illinois 61801	1
Troy, New York 12181 Dr. John T. Yates	1	Dr. W. Kohn University of California (San Diego) Department of Physics	
National Bureau of Standards Department of Commerce		La Jolla, California 92037	1
Surface Chemistry Section Washington, D.C. 20234	1	Dr. R. L. Park Director, Center of Materials Research University of Maryland	
Dr. Theodore E. Madey Department of Commerce National Bureau of Standards Surface Chemistry Section		College Park, Maryland 20742	1
Washington, D.C. 20234	1		
Dr. J. M. White University of Texas Department of Chemistry			
Austin, Texas 78712	1		

TECHNICAL REPORT DISTRIBUTION LIST

No. Co	op1es	No.	Cop1=
Dr. W. T. Peria Electrical Engineering Department University of Minnesota Minneapolis, Minnesota 55455	1	Dr. Leonard Wharton James Franck Institute Department of Chemistry 5640 Ellis Avenue Chicago, Illinois 60637	1
Dr. Narkis Tzoar City University of New York Convent Avenue at 138th Street New York, New York 10031	1	Dr. M. G. Lagally Department of Metallurgical and Mining Engineering University of Wisconsin	
Dr. Chia-wei Woo Northwestern University		Madison, Wisconsin 53706	1
Department of Physics Evanston, Illinois 60201 Dr. D. C. Mattis	1	Dr. Robert Gomer James Franck Institute Department of Chemistry 5640 Ellis Avenue	
Yeshiva University Physics Department		Chicago, Illinois 60637	1
Amsterdam Avenue & 185th Street New York, New York 10033	1	Dr. R. F. Wallis University of California (Irvine) Department of Physics	
Dr. Robert M. Hexter University of Minnesota		Irvine, California 92664	1
Department of Chemistry Minneapolis, Minnesota 55455	1		

TECHNICAL REPORT DISTRIBUTION LIST

No. Copies	1	lo. Copis
Dr. Stephen H. Carr Department of Materials Science Northwestern University Evanston, Illinois 60201 1	Dr. G. Goodman Globe Union Inc. 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. M. Broadhurst Bulk Properties Section National Bureau of Standards U.S. Department of Commerce Washington, D.C. 20234 2	Picatinny Arsenal SMUPA-FR-M-D Dover, New Jersey 07801 Attn: A. M. Anzalone Bldg. 3401	1
Dr. C. H. Wang Department of Chemistry University of Utah Salt Lake City, Utah 84112	Dr. J. K. Gillham Princeton University Department of Chemistry Princeton, New Jersey 08540	1
Dr. T. A. Litovitz Department of Physics Catholic University of America Washington, D.C. 20017 Dr. R. Y. Subramanian	Douglas Aircraft Co. 3855 Lakewood Boulevard Long Beach, California 90846 Attn: Technical Library Cl 290/36-84 AUTO-Sutton	1
Washington State University Department of Materials Science Pullman, Washington 99163 1 Dr. M. Shen	Dr. E. Baer Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	
Department of Chemical Engineering University of California Berkeley, California 94720 1	Dr. K. D. Pae Department of Mechanics and Material Rutgers University	
Dr. V. Stannett Department of Chemical Engineering North Carolina State University Raleigh, North Carolina 27607 1	New Brunswick, New Jersey 08903 NASA-Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135	
Dr. D. R. Uhlmann Department of Metallurgy and Material Science Center for Materials Science and Engineering Massachusetts Institute of Technology Cambridge, Massachusetts 02139	Attn: Dr. T. T. Serofini, MS-49-1 Dr. Charles H. Sherman, Code TD 121 Naval Underwater Systems Center New London, Connecticut	1
Naval Surface Weapons Center White Oak Silver Spring, Maryland 20910 1 Attn: Dr. J. M. Augl Dr. B. Hartman	Dr. William Risen Department of Chemistry Brown University Providence, Rhode Island 02912	1

No. Copi	es	<u> 1</u>	No. Copie
Dr. Alan Gent Department of Physics University of Akron Akron, Chio 44304	1	Dr. W. A. Spitzig United States Steel Corporation Research Laboratory Monroeville, Pennsylvania 15146	1
Mr. Robert W. Jones Advanced Projects Manager Hughes Aircraft Company Mail Station D 132 Culver City, California 90230 Dr. C. Giori	1	Dr. T. P. Conlon, Jr., Code 3622 Sandia Laboratories Sandia Corporation Albuquerque, New Mexico 87115 Dr. Martin Kaufmann, Head Materials Research Branch, Code 4542	1
IIT Research Institute 10 West 35 Street Chicago, Illinois 60616	1	Naval Weapons Center China Lake, California 93555	1
Dr. M. Litt Department of Macromolecular Scie Case Western Reserve University Cleveland, Ohio 44106	ence 1	Dr. T. J. Reinhart, Jr., Chief Composite and Fibrous Materials Branck Nonmetallic Materials Division Department of the Air Force Air Force Materials Laboratory (AFSC) Wright-Patterson Air Force Base, Ohio	1
Dr. R. S. Roe Department of Materials Science and Metallurgical Engineering University of Cincinnati Cincinnati, Ohio 45221	1	Dr. J. Lando Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	
Dr. L. E. Smith U.S. Department of Commerce National Bureau of Standards Stability and Standards Wasnington, D.C. 20234	1	Dr. J. White Chemical and Metallurgical Engineering University of Tennessee Knoxville, Tennessee 37916	1
Dr. Robert E. Cohen Chemical Engineering Department Massachusetts Institute of Techno Cambridge, Massachusetts 02139	ology 1	Dr. J. A. Manson Materials Research Center Lehigh University Bethlehem, Pennsylvania 18015	1
Dr. David Roylance Department of Materials Science of Engineering Massachusetts Institute of Techno Cambridge, Massachusetts 02039		Dr. R. F. Helmreich Contract RD&E Dow Chemical Co. Midland, Michigan 48640	1

" 表示

THE RESIDENCE OF THE PARTY OF T